




# Architectural Powder Coatings




## Coating Selection Guide

<b>Hentzen Series Identification</b>	Dura-Zen™ 500	Dura-Zen™ 400	Dura-Zen™ 300
<b>Voluntary Specification</b>	AAMA 2605	AAMA 2604	AAMA 2603
<b>Film Thickness</b>			
Powder Specification	2 to 4 mils	2 to 4 mils	2 to 4 mils
<b>Dry Film Hardness</b>			
Specification -F minimum	2H-4H	2H-4H	2H-4H
<b>Film Adhesion</b>			
Dry Adhesion	Pass	Pass	Pass
Wet Adhesion	Pass	Pass	Pass
Boiling Water	Pass	Pass	N/A
<b>Impact Resistance</b>			
Gardner Impact	Pass	Pass	Pass
<b>Chemical Resistance</b>			
Muriatic Acid	Pass	Pass	Pass
Mortar	Pass	Pass	Pass
Nitric Acid	Pass	Pass	N/A
Detergent	Pass	Pass	Pass
Window Cleaner	Pass	Pass	N/A
<b>Corrosion Resistance</b>			
Humidity Resistance	4000 Hours	3000 Hours	1500 Hours
Cyclic Corrosion Resistance			
ASTM G85	2000 Hours		
Salt Spray Resistance ASTM B117		3000 Hours	1500 Hours
<b>South Florida Exposure</b>	10 Years	5 Years	1 Year

# Architectural Coatings



Bone White




Ivory



Sandstone



Sierra Tan



Milk White



Seawolf



Slate Gray



Charcoal Gray



Military Blue



Interstate Blue



Classic Bronze



Sepia Brown



Hemlock Green



Interstate Green



Forest Green



Hartford Green



River Rouge Red



Boysenberry



Medium Bronze



Black Satin

Actual coating colors may vary slightly from color samples.

## Architectural Powder Coatings

Add aesthetic appeal to your project. We offer 20 standard colors, formulated in three grades to meet your weathering and performance requirements.

**Dura-Zen™ 300 Polyester Architectural Grade powder coatings** are designed to meet or exceed the AAMA 2603 performance specifications. They provide good color and gloss retention.

**Dura-Zen 400™ Super Durable Polyester Architectural Grade powder coatings** are designed to meet or exceed the AAMA 2604 performance specifications. They provide better weatherability with a higher resistance to fading and chalking, and a higher level of gloss retention.

**Dura-Zen™ 500 Fluoropolymer Architectural Grade powder coatings** are designed to meet or exceed the AAMA 2605 performance specifications. They are high performance fluoropolymer coatings, providing superior weatherability. They provide the highest level of resistance to fading and chalking, and the highest level of gloss retention.



**Hentzen Coatings Inc. Corporate Headquarters**  
6937 West Mill Road, Milwaukee, WI 53218-1225  
P 414.353.4200 F 414.353.0286

**Milwaukee Powder Plant**  
8200 North Faulkner Road, Milwaukee, WI 53224  
P 414.353.4200 F 414.353.0286

[Hentzen.com](http://Hentzen.com)

1500 Lathem Street  
Batavia, IL 60510-1449  
P 414.353.4200 F 630.879.2954

307 Echelon Road  
Greenville, SC 29605  
P 864.299.2819 F 864.299.2820

5182 126th Avenue North  
Clearwater, FL 33760  
P 727.572.4474 F 727.572.4598

**Hentzen de México S. de R.L. de C.V.**  
Carretera Estatal hacia los Cues #431, Km 2 + 200 Lote 15 Bodega #1  
Col. Parque Tecnológico Innovación, El Marques Queretaro C.P. 76246  
Tel: 52 ( 442 ) 221-5821 and 52 ( 442 ) 221-6282

**China, 9 Buildings, No. 1**  
Zhongxing East Road  
Lishui Economic Development Zone  
Nanjing City, Jiangsu Province

